



ROSSROOF
GROUP

LIGHT REFLECTANCE AND TOTAL SOLAR ABSORPTION VALUES

SATIN FINISH	Light Reflectance ¹	Total Solar Absorption ²
Beige	32.9	66.8
Ebony	7.9	91.9
Grey Friars	9.9	89.9
Ironsand	8	90
Karaka	8	90
Mist Green	24.9	74.9
New Denim Blue	10.9	88.9
Permanent Green	10.9	88.9
River Gum	19.9	79.9
Scoria	9.9	89.9
Terracotta	22.9	76.9
Wizard	12	88
Flax	7.9	91.9
Sandstone Grey	25	75
Windsor Grey	12	88
Lignite	11	89
Desert Sand	27.9	71.9
Textured Finish		
Ashwood	16	82.7
Autumn	6.4	90.2
Beechwood	6.4	90.6
Brownbark	6.4	90.6
Cedar	8	89.8
Charcoal	4.2	94.4
Coffee Brown	6.4	90.2
Ember	6.6	91.6
Forest	6	91.8
Greenstone	6.5	90.2
Mesquite	3.8	93.2
Olive	5	92.6
Silver Grey	13	84.5
Slate	11	87.7
Terracotta	8.5	86.5
Walnut	6.5	90.2
Weathered Timber	11	86.5
Clay	14	84.6
Sunset	7	90.5
Midnight Blue	7	90.5
Sorrento	8.5	86.5
Pisa	7	90.5
Firenze	7	90.5
Tuscany	13	85.5
Lisbon	13	85.5
Province	13.5	85
1. Light Reflectance Value (LRV) is total visible light from a illuminated surface, using Colorimeter ASTM C609 - 8		
2. Total Solar Absorption Value (TSA) is Solar Absorption, using Reflectance values / Emmissivity ASTM E1981		